


FAMILY POOLS INC.

873 SW South Macedo Blvd.
Pt. St. Lucie, FL 34983
License # CPC1456929
1-866-294-4011
772-785-9558 fax



Instructions for newly plaster pool for Home Owner

Follow these simple instructions to insure the longest life of your Family Pool finish,

1. Refill pool —**DO NOT** stop the water flow! You may see gray tinting and color Distortion until pool is full-----*Don't be alarmed!* (If you have one available, add a second hose to expedite the filling process.)
2. Fill to customary level and **CALL THE OFFICE!**
3. At this time we will add the chemicals as needed. We will also do all clean-up and necessary touch-ups. After the initial start-up, the Chemicals and the normal maintenance become the Homeowners Responsibility
4. Run filter for 48 hours.
5. Brush pool to the main drain at least 2-3 times for the first couple of days to eliminate residue. Clean / backwash filter after each brushing so as not to clog up and destroy filter,
6. After 3 days, add chlorine SLOWLY and adjust pH as needed "**DO NOT SHOCK WITH CHLORINE**"
7. It is recommended to keep the PH low (7.2) for the first two weeks, to help the curing process and prevent staining.
8. Do Not Attempt To Turn on The Light Until The Pool Is Full!! Water cooled light Will be damaged if turned on in dry pool.

CHEMICAL PARAMETERS TO MAINTAIN

	<i>Minimum</i>	<i>Ideal</i>	<i>Maximum</i>
<i>Chlorine</i>	<i>1.0</i>	<i>1,5</i>	<i>3.0</i>
<i>PH</i>	<i>7.2</i>	<i>7.5</i>	<i>7.8</i>
<i>Cyanuric Acid ppm (stabilizer)</i>	<i>30</i>	<i>40</i>	<i>SO</i>
<i>Total Alkalinity ppm</i>	<i>80</i>	<i>100</i>	<i>120</i>
<i>Calcium Hardness ppm</i>	<i>150</i>	<i>200</i>	<i>250</i>

**ppm (parts per million)*